


Belsorp Adsorption/Desorption Data Analysis Software - Ver 6.1.0.4

BEL Japan, Inc.



Langmuir-Plot

Adsorptive N₂

Adsorption temperature 77 [K]

○ 1207682-GMSI-N-2-N2 Test.DAT

1207682-GMSI-N-2-N2 Test

Catalyst Evaluation Department

Degassed @305C for 3h

, Vacuum degree before measurement: 7.161E-5Pa

Sample weight	0.3142	[g]	Date of measurement	12/02/27
Saturated vapor pressure	88.493	[kPa]	Time of measurement	25:24:49
V_m	67.432	[cm ³ (STP) g ⁻¹]	$a_{s,Lang}$	293.50 [m ² g ⁻¹]
B	0.2405			

احمد فضل الشبي