


Belsorp Adsorption/Desorption Data Analysis Software - Ver 6.1.0.4

BEL Japan, Inc.



● 1207682-GMSI-N-2-N2 Test.DAT

1207682-GMSI-N-2-N2 Test
Catalyst Evaluation Department
Degassed @305C for 3h
Vacuum degree before measurement: 7.161E-5Pa

Sample weight	0.3142	[g]	Date of measurement	12/02/27
Saturated vapor pressure	88.493	[kPa]	Time of measurement	25:24:49
V_p	0.4504	[cm ³ g ⁻¹]	$r_{p,peak}(Area)$	3.52 [nm]
a_p	237.52	[m ² g ⁻¹]		

أحمد فضل المولى