


Belsorp Adsorption/Desorption Data Analysis Software - Ver 6.1.0.4

BEL Japan, Inc.



BJH-Plot

Desorption branch

Adsorptive N2

Adsorption temperature 77 [K]

● 1207682-GMSI-N-2-N2 Test.DAT

1207682-GMSI-N-2-N2 Test
Catalyst Evaluation Department
Degassed @305C for 3h
Vacuum degree before measurement: 7.161E-5Pa

Sample weight	0.3142 [g]	Date of measurement	12/02/27
Saturated vapor pressure	88.493 [kPa]	Time of measurement	25:24:49

V_p	0.4504 [cm ³ g ⁻¹]	a_p	237.52 [m ² g ⁻¹]
-------	---	-------	--

أحمد فضل الهادي