


Belsorp Adsorption/Desorption Data Analysis Software - Ver 6.1.0.4

BEL Japan, Inc.



t-Plot

Adsorption branch

Adsorptive N₂

Adsorption temperature 77 [K]

○ 1207682-GMSI-N-2-N₂ Test.DAT

1207682-GMSI-N-2-N₂ Test
Catalyst Evaluation Department
Degassed @305C for 3h
Vacuum degree before measurement: 7.161E-5Pa

Sample weight	0.3142 [g]	Date of measurement	12/02/27
Saturated vapor pressure	88.493 [kPa]	Time of measurement	25:24:49

a_1	201.19 [m ² g ⁻¹]	V_1	0.0000 [cm ³ g ⁻¹]
-------	--	-------	---

احمد فضل انصاری