


Belsorp Adsorption/Desorption Data Analysis Software - Ver 6.1.0.4

BEL Japan, Inc.



BJH-Plot

Adsorption branch

Adsorptive N2

Adsorption temperature 77 [K]

○ 1207675(2)-GMSI-P-N2 Test.DAT

1207675(2)-GMSI-P-N2 Test
Catalyst Evaluation Department
Degassed @305C for 3h
Vacuum degree before measurement: 6.041E-5Pa

Sample weight	0.2720 [g]	Date of measurement	12/02/20
Saturated vapor pressure	89.311 [kPa]	Time of measurement	23:24:46

V_p	0.6390 [cm ³ g ⁻¹]	a_p	316.37 [m ² g ⁻¹]
-------	---	-------	--

اعند فضل الپپی