


3elsorp Adsorption/Desorption Data Analysis Software - Ver 6.1.0.4

BEL Japan, Inc.



BJH-Plot

Desorption branch

Adsorptive N2

Adsorption temperature 77 [K]

• 1207675(2)-GMSI-P-N2 Test.DAT

1207675(2)-GMSI-P-N2 Test
Catalyst Evaluation Department
Degassed @305C for 3h
Vacuum degree before measurement: 6.041E-5Pa

Sample weight	0.2720	[g]	Date of measurement	12/02/20
Saturated vapor pressure	89.311	[kPa]	Time of measurement	23:24:46
V_p	0.6614	[cm ³ g ⁻¹]	$r_{p,peak} (Area)$	4.02 [nm]
a_p	369.07	[m ² g ⁻¹]		

استمد فضل الهمي