


Belsorp Adsorption/Desorption Data Analysis Software - Ver 6.1.0.4

BEL Japan, Inc.



t-Plot

Adsorption branch

Adsorptive N₂

Adsorption temperature 77 [K]

○ 1207675(2)-GMSI-P-N2 Test.DAT

1207675(2)-GMSI-P-N2 Test

Catalyst Evaluation Department

Degassed @305C for 3h

, Vacuum degree before measurement:6.041E-5Pa

Sample weight	0.2720 [g]	Date of measurement	12/02/20
Saturated vapor pressure	89.311 [kPa]	Time of measurement	23:24:46

a_1	276.04 [m ² g ⁻¹]	V_1	0.0000 [cm ³ g ⁻¹]
-------	--	-------	---